

Domtar POS 74C - 3.2

Product Specifications

Caliper	Basis Weight	Brightness (UV Included)	Thermal Response - Nominal				Gurley Stiffness Nominal (mg)		Elmendorf Tear Nominal (g)		Parker Print Surf
			Static - (°C ± 5°)		Dynamic - Atlantek 400 (mJ/mm ²)		MD:	CD:	MD:	CD:	
			0.2 ODU	85	0.2 ODU	5.4					
mils	17 x 22— 500 (lbs)	>85	1.0 ODU	137	1.0 ODU	8.8	88	42	53	54	<2.20
3.20 3.00 - 3.40	19.7 18.6 - 20.8		Max. Density	1.1	Max. Density	1.46					
µm	g/m ²		Required Temp.	149	Energy Req.	16.0					
81.3 76.2 - 86.4	74.0 69.9 - 78.1										

Features:

- Bond-like feel
- Bar code and graphics imaging
- Bright white appearance
- Flexographic printable front and back
- Lithographic printable back side only

Ideal For:

- Chart applications
- Kiosks
- Parking receipts

Environmental Characteristics:

- Produced without the use of bisphenol A (BPA)

